

Technical Data Sheet

Product Code:	G1.00.80ET.NC.XX00.TH	
Applications:	PET Bottles and Sheet manufacturing	
Material form:	Pellets ~ 4mm	
Product, Colour:	Crystal clear	
Origin of material:	100% Ocean bound material	

rPET clear (FDA)

regranulated polyethyleneterephthalate from Ocean bound waste (crystallized)

Physikalische / Mechanische Eigenschaften Physical / Mechanical Properties		measured at 23°C / 50%rh	
Eigenschaft / Property	Prüfung / Test method	Wert Value	Einheit Unit
Intrinsische Viskosität Intrinsic viscosity (IV)	DIN EN ISO 1628/5	0.80 ± 0.03	dl/g
Dichte Density	DIN EN ISO 1183-1	1.33 ± 0.02	g/cm³
Aschengehalt Ash Content	DIN EN ISO 3451-1	< 0.009	%
Feuchtegehalt Bulk Moisture	DIN EN ISO 62 - D	<0.02	%
L Color	IR-004 / CIE Lab	>70.0	Amorphous Chips
b Color	IR-004 / CIE Lab	0 ± 2	Amorphous Chips
Chips/gm (Balance)	IR-007 Weighment Method	50-65	nos/gm
Kristallinität Crystallinity	IR-005 Gradient Coloumn	>50	%
Acetaldehyde	GC-MS	<1.0	ppm

LNO received from US FDA (PNC 2411).

Indonesia FDA (BPOM Regulation No 20 in 2019 about Food Packaging).

FDA- Regulation 21 CFR § 177.1630 [section (f) & (g)] in the current valid version/s

European Union (EU) EC10/2011 (including latest amendments of 2019).

EU REACH Regulation (EC) No 197/2006 Article 33 (1) for SVHCs (219) as per 25th SVHC in the Candidate List (2021.07) ROHS DIRECTIVE (2011/65/EU): Restriction of use of certain hazardous substances in Electrical and Electronic Equipment ROHS DIRECTIVE (2011/65/EU) and amendment commission delegated directive EU 2015/863 with effective from 22 July 2019: Phthalate Content

CONEG Legislation in the USA as well as EN712015/863/EU (Heavy Metals)

GRS certified

Please note: The recommendations for the use of our products are based on tests believed to be reliable. However, we do not guarantee the results to be obtained by others under different conditions. Although such information is, to the best of our knowledge and internal measurements, accurate and reliable as of the date hereof, no guarantee is made as to the suitability, accuracy, reliably and completeness of such information for its particular use. These are only approximate values.